

MEGAROLL 2 mm

TECHNICAL DATA SHEET FOR UNDERLAYMENT

Agglomerated cork produced with 0.5/2mm granulated cork binder-polyurethane

Physical properties

Density (minimum):	+/-180 kg/m ³
Compression (%)	25 - 40
Recovery (%):	> = 75
Boiling water:	No desintegration
Tensile strength:	2 – 7kg/cm ²
Thermal conductivity (kcal/mh°c):	0.0410
Impact sound insulation	min 15db