



MEGAROLL

TECHNICAL DATA SHEET FOR GRADE MR 35

Agglomerated cork produced with 1/3mm granulated cork binder-polyurethane

Physical properties

Density (minimum):	180 kg/m3
Compression (%)	25 - 35
Recovery (%):	> = 75
Boiling water:	No desintegration
Tensile strength:	min. 3 kg/cm2
Thermal conductivity (kcal/mh°c):	0.0410
Impact sound insulation	17db